



Elliptical-clad Polarization Maintaining Gyroscope & Sensor Fibers

Nufern's elliptical clad PM Gyroscope fibers have high birefringence and are designed for gyroscope and sensor applications. These fibers feature good bending performance and are optimized for either 850 nm or 1300 nm wavelength operation. The 850 nm optimized fiber has a 40 μm clad diameter and the 1300 nm optimized fiber has an 80 μm clad diameter. Both are ideally suited for applications requiring a small form factor.

Typical Applications

- Fiber optic gyroscopes (FOGs)
- Fiber optic voltage and current sensors
- Laser pigtailed
- Small form factor couplers
- Specialty sensors

Features & Benefits

- High birefringence — Less gyroscope drift
- Bend insensitive — Smaller diameter coils possible
- Excellent crosstalk over temperature range — Ensures performance in harsh environments
- Nufern proprietary coating — Optimized for gyroscope applications

Optical Specifications

	PME850G-40/100-5	PME1300G-80/170-5
Operating Wavelength	810 – 870 nm	1290 – 1340 nm
Core NA	0.180	0.180
Mode Field Diameter	4.0 \pm 0.5 μm @ 850 nm	6.0 \pm 0.5 μm @ 1300 nm
Cutoff	720 \pm 60 nm	1230 \pm 50 nm
Core Attenuation	\leq 12.0 dB/km @ 820 nm	\leq 2.0 dB/km @ 1300 nm
Beat Length	\leq 2.0 mm @ 850 nm	\leq 1.2 mm @ 633 nm
H-Parameter	\leq 5.00000 \times 10 ⁻⁵ m ⁻¹ @ 850 nm	\leq 3.00000 \times 10 ⁻⁵ m ⁻¹ @ 1300 nm
Normalized Cross Talk	\leq - 25.0 dB at 100 m @ 630 nm	\leq - 25.0 dB at 100 m @ 1300 nm

Geometrical & Mechanical Specifications

Cladding Diameter	40.0 \pm 1.0 μm	80.0 \pm 1.0 μm
Core Diameter	3.5 μm	6.0 μm
Coating Diameter	100.0 \pm 5.0 μm	170.0 \pm 5.0 μm
Core/Clad Offset	\leq 1.50 μm	\leq 2.00 μm
Operating Temperature Range	-60 to 105 °C	-60 to 105 °C
Proof test Level	\geq 100 kpsi (0.7 GN/m ²)	\geq 100 kpsi (0.7 GN/m ²)



JAPAN
DEVICE

URL: <http://j-device.com>

営業: sales@j-device.com

TEL: 03-6262-3424

日本デバイス株式会社

FAX: 03-6800-5883

Coating Requirements: UV cured dual acrylate coating



7 Airport Park Road, East Granby, CT 06026 • 860.408.5000 • Toll-free 866.466.0214 • Fax 860.844.0210 • E-mail info@nufern.com • www.nufern.com • Nufern products are manufactured under an ISO 9001:2008 certified quality management system.

Custom developed fiber (FUD) specifications are subject to change without notice. Other configurations such as alternative form factors, optimized cut-off and UV cured color coating may be available. Let us know how Nufern can assist with your requirements.

